

**What is claimed is:**

1. A biodegradable recycled polyester resin, which is obtained by a process including the step of carrying out a reaction of a recycled aromatic polyester (A) with an aliphatic polyester (B) having a number-average molecular weight of 3,000 to 300,000 in a reaction ratio (weight ratio) of (A)/(B) = 95/5 to 5/95, thereby affording biodegradability to the recycled aromatic polyester (A).

2. A biodegradable recycled polyester resin according to claim 1, wherein the aliphatic polyester (B) is obtained from an aliphatic dicarboxylic acid component having 2 to 6 carbon atoms and an aliphatic glycol component having 2 to 4 carbon atoms.

3. A biodegradable recycled polyester resin according to claim 1, wherein the aliphatic polyester (B) is obtained by a process including the step of carrying out ring-opening copolymerization of a cyclic acid anhydride (C) and a cyclic ether (D), wherein the cyclic acid anhydride (C) includes succinic anhydride as a major component, and wherein the cyclic ether (D) includes ethylene oxide as a major component.

4. A biodegradable recycled polyester resin according to claim 2, wherein the aliphatic polyester (B) is obtained by a process including the step of carrying out ring-opening copolymerization of a cyclic acid anhydride (C) and a cyclic ether (D), wherein the cyclic acid anhydride (C) includes succinic anhydride as a major component, and wherein the cyclic ether (D) includes ethylene oxide as a major component.

5. A biodegradable recycled polyester resin according to claim 1, which has a structure such that the recycled aromatic polyester (A) and the aliphatic polyester (B) are arranged in a block form.

5

6. A biodegradable recycled polyester resin according to claim 2, which has a structure such that the recycled aromatic polyester (A) and the aliphatic polyester (B) are arranged in a block form.

10

7. A biodegradable recycled polyester resin according to claim 3, which has a structure such that the recycled aromatic polyester (A) and the aliphatic polyester (B) are arranged in a block form.

15

8. A biodegradable recycled polyester resin according to claim 4, which has a structure such that the recycled aromatic polyester (A) and the aliphatic polyester (B) are arranged in a block form.

20

9. A production process for a biodegradable recycled polyester resin, which comprises the step of carrying out a melting reaction of a recycled aromatic polyester (A) with an aliphatic polyester (B) in a heated state in a reaction ratio (weight ratio) of (A)/(B) = 95/5 to 5/95, wherein the aliphatic polyester (B) has a number-average molecular weight of 3,000 to 300,000.